

# PRODUCT INFORMATION



## PFF RESINCOTE GOLD

A modern blend of a traditional acid cure lacquer with a high solids content, which minimises VOC content and maximises film build.

### DESCRIPTION

A two-component high performance wood lacquer consisting of a resinous base material that cures chemically when the acid catalyst (hardener) is added. This chemical action, which is irreversible, gives RESINCOTE GOLD unique properties of flexibility and adhesion so necessary for floors and interior woodwork. Resistance to solvents is excellent, being unaffected by alcohol, fats and most acids. PFF RESINCOTE GOLD does not darken or yellow with age and is completely clear, enhancing the natural colour and grain of all types of wood.

### WHERE TO USE

Use on new and existing wood floors especially high traffic areas such as halls, stairs and kitchens. And on interior woodwork such as tables, bar tops, work surfaces, skirting boards and other hardwearing wood surfaces. Not recommended for use on wood treated with wood preservatives.

### FEATURES

Available in 2.5lt and 5lt packs in gloss and satin finishes RESINCOTE GOLD is packed complete with hardener, stirring stick and detailed user instructions (on can). The 'mix in the can' formula and stirring stick minimises the risk of contamination from dirty mixing bowls and implements. Easy to apply, the lacquer flows easily when applied by brush for fast coating and maximum film build.

FULL APPLICATION INSTRUCTIONS ON REVERSE



### SPECIFICATIONS

Type	:	Two component acid cure wood lacquer.
Coverage	:	Hardwood two coats 6m <sup>2</sup> /litre. Softwood three coats 4m <sup>2</sup> /litre.
Resistance to Wear	:	High
Resistance to Solvents	:	High
Application	:	Brush.
Drying Times	:	Surface dry 25 minutes. Hard dry 1 to 2 hours. Light use 6 hours. Fully cured 7 days.
Cleaning	:	PFF Resincote Brush Cleaner.
Flammability	:	Highly Flammable
VOC	:	High (25 to 50%).
Safety Data Sheet	:	010, 030, 040

### PRODUCT CODES

PSTK	Description	Case Qty	Case Weight
15001	Resincote Gold 2.5lt Gloss	4	13.24kg
15002	Resincote Gold 5lt Gloss	2	12.40kg
15011	Resincote Gold 2.5lt Satin	4	13.24kg
15012	Resincote Gold 5lt Satin	2	12.40kg
15130	Brush Cleaner 500ml	4	3.01kg
15140	Floor Finish Brush 10cm	20	2.58kg
15150	Tack Rag	25	0.70kg

## IMPORTANT INFORMATION

FLOOR TEAM PFF RESINCOTE GOLD is a two component, high performance lacquer that cures by chemical reaction between the resinous base material and the acid catalyst (hardener). If this reaction is contaminated the cure and adhesion of the PFF may be affected. Highly resinous or oily timber, new wood with a high moisture content, floors previously maintained with wax polishes, stains and fillers, dirty brushes and mixing bowls are all examples of possible sources of contamination. PFF RESINCOTE GOLD is not recommended for use on wood treated with wood preservatives. ALWAYS test for compatibility before full application. DO NOT apply below an ambient temperature of 10°C. For help and information contact the FLOOR TEAM helpline.

## COVERAGE

HARDWOOD : Two coats 2.5 litres covers approximately 15m<sup>2</sup>  
SOFTWOOD : Three coats 2.5 litres covers approximately 10m<sup>2</sup>

## PREPARATION OF SURFACES

The surface MUST be absolutely clean, dry and free from grease, fats, polish, old varnish or any other surface coating. If the wood was previously wax polished, clean thoroughly with a lint free cloth and a little white spirit before the final sanding. Allow the white spirit to dry thoroughly then give the wood a final light sanding. Remove all traces of dust by first vacuuming then wiping over with a FLOOR TEAM TACK RAG.

## TESTING

Test for compatibility before use. Test coat on a small area with 2 to 3 coats according to appearance required, carefully following the MIXING and APPLICATION instructions below. If any coat fails to cure properly DO NOT apply to the whole floor or wood surface, contact the FLOOR TEAM helpline for advice.

## MIXING

Mix in the can immediately prior to application. Slowly add the complete contents of the PFF RESINCOTE HARDENER bottle to the can of resin. Stir slowly using the stirring stick supplied until the contents of the tin becomes clear (the Satin finish will have a slight opaque appearance).

## APPLICATION

Must be carried out in well-ventilated conditions, which are dry and warm, not damp or humid. Apply direct from the can using a clean FLOOR TEAM FLOOR FINISH BRUSH or medium weight white bristle brush. Apply liberally and allow the PFF to flow across the surface and find its natural level. Excessive brushing is not necessary, as the PFF will flow easily.

Allow the PFF to dry hard, normally 2 hours and then apply the next coat as required. Lightly sand between coats of PFF if required for an exceptionally fine finish or if the time between coats is more than 3 hours. Vacuum and TACK RAG between coats to keep the surface free from dust.

After the last coat has been applied allow the PFF to cure for as long as possible before use - ideally overnight although the floor may be walked on in stocking feet once the PFF has dried hard. Avoid placing or moving heavy furniture and objects on the floor or surface, again for as long as possible. Full cure and resistance to water and other solvents is achieved after 7 days. Always wipe up spill liquids immediately in the first 7 days after application.

## MAINTENANCE

Sweep or vacuum regularly to remove grit and clean using a damp mop. PFF does not need polishing. Scuffmarks may be removed using a non abrasive cream cleaner.

## HEALTH & SAFETY

HARMFUL BY INHALATION AND IN CONTACT WITH SKIN. IRRITATING TO SKIN.

Keep out of reach of children. Keep away from sources of ignition. No Smoking. Keep container tightly closed. Do not breathe vapour and use only in well-ventilated areas. In case of insufficient ventilation in confined spaces and when applying to large surfaces use suitable respiratory equipment. Avoid contact with skin and eyes. Wear suitable gloves and eye protection. Wear suitable protective clothing.

## ENVIRONMENT

Remove as much PFF from brushes before cleaning with PFF RESINCOTE BRUSH CLEANER. Do not empty into drains or watercourses, or access routes to septic tanks. Local authorities have special facilities for the disposal of waste paints and varnishes. It is recommended that waste PFF be taken to your local household waste disposal site. To avoid the risk of spillage, always store and transport in a secure, upright position.

## FIRST AID, FIRE & CLEANING

**Eyes:** Rinse immediately with plenty of water and seek medical advice. **Skin:** Wash immediately with soap and plenty of water. **If Swallowed:** Do not induce vomiting, seek medical advice immediately and show this container or label. **Inhalation:** Remove to fresh air and obtain medical attention if there is any difficulty with breathing. **Fire:** In case of fire use carbon dioxide, dry chemical, foam, sand or earth. Never use water. **Cleaning:** To clean brushes use FLOOR TEAM PFF RESINCOTE BRUSH CLEANER. Do not use any other type of solvent or brush cleaner, allow to dry thoroughly before re-using.

## HELPLINE

For help and information on sanding and finishing your floor or other wood surfaces call the FLOOR TEAM helpline in the UK on Tel: 01923 332424 Fax: 01923 332425 or E-mail: [floorteam@hiretech.co.uk](mailto:floorteam@hiretech.co.uk)

## MADE IN UK

Floor Team and Hiretech are registered trademarks of Hire Technicians Group Ltd.

The specifications of the products described in this document are subject to change without prior notice.